

**TECHNICAL CHARACTERISTICS**  
**CARATTERISTICHE TECNICHE**

**art. DAYTON**

TEST TYPES / TIPO DI TEST	ASPECT	NORM	UNIT	STANDART TEST
WEIGHT / PESO		750±55	g/m <sup>2</sup>	ISO 2286-2
THICKNESS / SPESSORE		1,20±0,10	mm	ISO 2286-3
TEAR STRENGHT / RESISTENZA ALLO STRAPPO	ACROSS	>40	N	ISO 4674-1
	ALONG	>50	N	ISO 4674-1
TENSILE STRENGHT / RESISTENZA ALLA TRAZIONE	ACROSS	>450	N	ISO 1421
	ALONG	>450	N	ISO 1421
ELONGATION AT BREAK / ALLUNGAMENTO ALLA ROTTURA	ACROSS	140±20%	%	ISO 1421
	ALONG	120±20%	%	ISO 1421
ADHESION / ADERENZA		>45	N	ISO 2411
MARTINDALE - ABRASIONE		>150.000	RUB(12kPa)	ISO 5470-2
COLOR FASTNESS TO RUBBING / SOLIDITA' AL COLORE	DRY	>=5	GS	ISO 105X12
	WET	>=5	GS	ISO 105X12
LIGHT FASTNESS / SOLIDITA' ALLA LUCE	LIGHT COLORS	>=5	BW	ISO 105B02
	DARK COLORS	>=6	BW	ISO 105B02
ANTIMICROBIAL & ANTIFUNGAL TRATTAMENTO ANTIMICROBICO		Good Effect		ISO 20645: 2002
		Good Effect		
		Good Effect		
FLAME RETARDANCY / CERTIFICATI IGNIFUGITA'	IMO FTP Code Annex 1 Part 8 FMVSS 302 (FR Standart of Motor Vehicles) 5852 Part 1 Ignition Source 0,1 (Cigarette & Match) 1021 part 1 and 2			BS EN
DISINFECTION RECOMMENDATION / NORME DI PULIZIA	Our products are alcohol resistant and easy to clean. It is effective against alcohol-containing wipes, alcohol-free PUR wipes, and disinfectants containing a mixture of dilute acid and alcohol. It should be tested on a small piece before use. Use diluted if possible and do not let them act for a long time.			

**COMPOSITION - COMPOSIZIONE**

VINYL

**BACKING - SUPPORTO**

%100 POLYESTER

MAGICOTEX SRL

VIA MAESTRI DEL LAVORO 200/D - CASTEL SAN PIETRO TERME (BO)

PHONE /TELEFONO +39 051 941253

FAX / FAX +39 051 941283

EMAIL: [info@magicotex.com](mailto:info@magicotex.com)

[www.magicotex.com](http://www.magicotex.com)