



ENDUCROSS

GRIFFINE

ISO 9001 ISO TS 16949 ISO 14001

INDUSTRY

composition: 89%PVC + 11% PA



Tests	Specification	Documents or norms	Comments
Visual and general properties			
total mass surfacic	700 +/- 50 g/m2	ISO 2286	
mass surfacic of the textile	80 +/- 10 g/m2	ISO 2286	Fabric
total thickness	1,25 +/- 0,1 mm	ISO 2286	under 2kPa
color	in conformity	under light D65	
gloss	in conformity	under light D65	
Haptic or embossed surface	in conformity	under light D65	
mechanical properties			
Breaking strength WMD/AMD	>= 35daN >=20daN	ISO 1421	
Elongation at break WMD/AMD	>= 110% >= 180%	ISO 1421	
Tear strength WMD/AMD	>= 3 daN >= 2 daN	EN 4674-1 méthode A	
Toughness properties			
Adherence WMD/AMD	>= 3daN/5cm	ISO 2411	
Scrub test (creasing behaviour)	>50 000	ISO 5981	
Light and colour fastness to artificial weathering (Xenotest)	>=6	ISO 105 B02/B04	75h/70°C/65% HR
Color fastness to rubbing dry (crockmeter)	>= 4/5	ISO 105 X12	10 cycles
Color fastness to rubbing wet (crockmeter)	>= 4/5	ISO 105 X12	10 cycles
Staining resistance against blood and urine	0	0	
Fire resistance properties			
Other properties			
Certification			
Oekotex	classe 4	Standard 100	
REACH	in conformity	DIRECTIVE 1907/2006/EC	
OEHHA - Proposition 65 (USA)	in conformity	Safe Drinking Water and Toxic Enforcement Act of 1986	
<p><i>The best cleaning products are a pH neutral soap and a soft brush. Not all strong detergents are recommended by Cotting (please refer to our sample card). We cannot be held responsible for migration problems generated by dyes of poor quality</i></p>			
indice A du10/11/2016			

These values are given for information only and are based on statistical data from our laboratory. For special specifications, we can make a specific and tailored study. We reserve the right to change some of the values without preconditions, to the extent that the product is suitable for the intended use.

GRIFFINE Enduction 182 route de Paris F-95420 NUCOURT France

