

# Magicotex



## PRODUCT SPECIFICATION SHEET



<b>Article</b>	<b>VOYAGER</b>
<b>Primary use</b>	<b>Hospitality, Contract, Residential Upholstery, Corporate.</b>
<b>Origin</b>	Italy
<b>Custom tariff</b>	59031090
<b>Roll length</b>	30 LM
<b>Useful width (± 3cm)</b>	140 cm
<b>Compliant with</b>	<b>EU: REACH</b> <b>US: PROPOSITION 65 - Law AB 2998</b>
<b>Environmental concern</b>	Phthalates free - Heavy metal free - Azo free. Produced on site partially powered by solar panels.

Technical properties	Standard	Unit	Values
Total weight ± 5%	UNI EN ISO 2286-P:2°	gr/m2	720
Backing's weight ± 5%	UNI EN ISO 2286-P:2°	gr/m2	70
Thickness ± 0,1	UNI EN ISO 2286-P:3°	mm	1,00
Density	-----	gr/m3	0,72
Coating composition	100% VINYL (Phthalates free)		
Backing composition	100% PA		
Full composition	92% VINYL / 8% PA		
Tensile resistance / warp side	UNI EN ISO 1421	N/5cm	400
Tensile resistance / weft side	UNI EN ISO 1421	N/5cm	150
Ultimate elongation / warp	UNI EN ISO 1421	%	100
Ultimate elongation / weft	UNI EN ISO 1421	%	200
Tear resistance / warp	UNI EN ISO 4674-1 meth.B	N	15
Tear resistance / weft	UNI EN ISO 4674-1 meth.B	N	15
Peel adhesion / warp	UNI EN ISO 2411	N/5cm	15
Peel adhesion / weft	UNI EN ISO 2411	N/5cm	15
Bally at + 23° C	UNI 4818 - P:13	cycles	100.000
Bally at - 10° C	UNI 4818 - P:13	cycles	15.000
Xeno test	UNI EN ISO 4892-2 B2	Grey scale	4/5
Colour fastness to rubbing with alcohol	UNI EN ISO 105-X12	Grey scale	4
Colour fastness to rubbing with 3% Sodium Hypochlorite	UNI EN ISO 105-X12	Grey scale	4
Martindale	UNI EN ISO 12947-2	cycles	≥ 100.000
Flame retardant	<b>IT:</b> Classe 1 I M - UNI 9175 <b>US:</b> TB 117 : 2013 - FMVSS 302 <b>EU:</b> UNI EN 1021 part 1 & part 2 : 2014 <b>UK:</b> BS 5852 : 2006 source 0 & source 1		
Cleaning	Surface washable with water and neutral soap. For disinfection, sanitization and cleaning suggestions refer to the appropriate annex via our web site.		

The surface of this article is treated with an anti-ink finish. Dab with alcohol to remove most difficult stains.  
These are statistic average results. We reserve the right to make changes without notice insofar as the product remains suitable for the intended use.